



TECHNICAL DATA SHEET

CI/SfB

76.7

SAFETY AND SECURITY FILM

10300 SERIES INTERNAL ANTI-SHATTER 175 MICRON FILM

InterLace safety and security window films are designed to make glass safer, both by strengthening it against breakage and helping hold dangerous shards of shattered glass in situations where breakage does occur.

Tested and certified to EN 12600 Class 1B1, 10300 Series Internal Anti-Shatter 175 Micron Film is used to help comply with current government guidelines for bomb blast protection. InterLace safety and security window films are suitable for use in many applications in the workplace and home. Other benefits can include improved security by creating a deterrent to “smash-and-grab” crime, and providing protection against the vandalism of glass through graffiti such as the etching or scratching of glass.

FEATURES

- High optical clarity
- Quick, retro-fit installation
- Scratch-resistant
- Screening of harmful UV rays

BENEFITS

- Clear, non-tinted appearance on glass
- Can be used where costly and disruptive large-scale replacement of existing glazing is not a viable option
- Suitable for most non-abrasive window-cleaning methods
- Reduced fading of interior furnishings



For specifications and drawings please visit our website www.interlaceblinds.com

INTERLACE WARRANTY

Safety and security films are covered against defective manufacturing for 12 months from the date of installation. This warranty does not cover misuse, damage caused after installation, or vandalism.

InterLace liability is limited to the replacement of defective products like for like only. InterLace is committed to a program of continuous product improvement.

Please be advised that specifications, performance, appearance, and dimensions of InterLace products are subject to change without notice. InterLace reserves the right to the final decision in the event of any warranty claim.

PERFORMANCE DATA

SOLAR ENERGY	Transmitted	77%
	Reflected	9%
	Absorbed	14%
VISIBLE LIGHT	Transmitted	87%
	Reflected (Interior)	11%
	Reflected (Exterior)	11%
UV Rejection	98%	
Glare Reduction	1%	
Shading Coefficient	0.92	
Solar Heat Gain Coefficient (G-Value)	0.80	
U-Value (W/m ² K)	6.07	
Total Solar Energy Rejected	20%	
Product Warranty*	12 months	

PHYSICAL PROPERTIES

Description	Clear
Film thickness	175-Microns (7-thou)
Structure	Single Ply
Tensile Strength	28,500 PSI
Break Strength	178 pounds per inch (width)
Adhesive Type	Acrylic Pressure Sensitive
Peel Strength	6 to 7 pounds per inch

NOTES

Test results are produced from film applied to 3mm clear single glass. Performance data is subject to change without prior notice. It is the users' responsibility to ensure the product is suitable for the intended use. The seller shall not be liable for any direct, indirect or consequential loss or damage howsoever arising.

SPECIFICATION

The film is to be installed to the interior surface of the glass, and the unique product roll numbers used are to be registered in accordance with the manufacturer's warranty procedure.

An exterior grade is available.
Refer to code: SA-175CL-eSR.



INTERLACE
EST. 1976

InterLace® Blinds Ltd, Cambridge CB21 4XN | T: 0800 619 6999 | sales@interlaceblinds.com | www.interlaceblinds.com

Call InterLace sales office on **0800 619 6999** to order samples or email your requirements to sales@interlaceblinds.com